

---

## GRIS STANSTEAD®

---

ASTM		Impérial	Métrique
Absorption massique	ASTM C97	0.26%	0.26%
Compression uniaxiale	ASTM C170	28 000Psi	193Mpa
Poids volumique	ASTM C97	166lb/ft <sup>3</sup>	2 659kg/m <sup>3</sup>
Module de rupture	ASTM C99	2050Psi	14.13Mpa

S'il vous plait prenez connaissance que les résultats de l'ASTM ci-dessus sont représentatifs de nos tests les plus récents. Vos résultats peuvent varier légèrement. Ces données sont présentées pour fin de référence seulement et sont basées sur des moyennes.

---

## STANSTEAD GREY®

---

ASTM		Imperial	Metric
Absorption by weight	ASTM C97	0.26%	0.26%
Compressive strength	ASTM C170	28 000Psi	193Mpa
Density	ASTM C97	166lb/ft <sup>3</sup>	2 659kg/m <sup>3</sup>
Modulus of rupture	ASTM C99	2050Psi	14.13Mpa

Please note that the above ASTM results are representative of our most recent tests. Your actual results may vary slightly.  
All figures are for reference only and are based on averages.



Rock of Ages Canada Inc.  
Stanstead, Québec, Canada  
Tel (800) 567 - 2793  
Tel (819) 876 - 2745  
Fax (819) 876 - 2234  
[www.rockofagescanada.com](http://www.rockofagescanada.com)